



TUNGSTEN COMPOUNDS

Number: MTC-QPP-FNS-FUS-03
 Issued date: 23.08.2021
 Revision no: 02
 Revised date: 06.04.2026

Blue Tungsten Oxide

Description of Product A finely divided, blue powder. It is primarily used in production of tungsten metal powder, fine tungsten carbide as well as wire products.



Chemical Characteristics

(Mass fraction in % [cg/g]; ppm [µg/g])

WO ₃ (calculated)	min. 99.8 %
NH ₃	max. 1700 ppm
Al	max. 5 ppm
As	max. 10 ppm
Bi	max. 5 ppm
Ca	max. 8 ppm
Cd	max. 5 ppm
Co	max. 5 ppm
Cu	max. 5 ppm
Cr	max. 5 ppm
Fe	max. 10 ppm
K	max. 10 ppm
Mg	max. 5 ppm
Mn	max. 5 ppm
Mo	max. 15 ppm
Na	max. 10 ppm
Ni	max. 5 ppm
P	max. 15 ppm
Pb	max. 5 ppm
S	max. 7 ppm
Sb	max. 5 ppm
Si	max. 10 ppm
Sn	max. 10 ppm
Ta	max. 6 ppm
Ti	max. 5 ppm
V	max. 15 ppm

Physical Characteristics

Fisher number	10 ÷ 20 µm
Apparent density	2.0 ÷ 3.0 g/cm ³
Specific surface	7 ÷ 11 m ² /g
Hall flow	≤ 50 s
Porosity	0.5 ÷ 0.7

TUNGSTEN COMPOUNDS

Number: MTC-QPP-FNS-FUS-03

Issued date: 23.08.2021

Revision no: 02

Revised date: 06.04.2026

- Packaging** 1,000 kg of BTO packed in bottom discharge bag with three layers. Other kinds of packaging are available on request.
- Storage and Handling** The user must observe all the relevant safety regulations in force in the country of use.